



Technical Data Sheet

70 GSM

Test Parameters	Unit	Test Method	Specifications	Tolerances (+/-)
Whiteness	CIE	ISO 11475	150	3 Units
Caliper	Microns	ISO 534	97	3 % REL
Moisture	%	ISO 287	4	1 % ABS
Opacity	%	ISO 2471	91	Min.
Brightness	%	ISO 2470	95	Min.

Maram copy papers come in 150 CIE and are machine-friendly papers offering superior clarity in print. Maram is also cost effective, jam & dust free and is known for faster productivity.

Maram's High opacity allows for reverse printing to save paper. Perfect for use in photocopy machines, laser printers & Ink jets, mainly used in offices and for multi-purpose usage. This kind of paper is very popular amongst export markets.



Kaagaz Trading L.L.C

City Bay Business Center - Office No: 507
5th Floor, Opposite Abu Hail Metro Station
Dubai, United Arab Emirates

+971 4 222 6779 +971 50 279 6552 yuvraj.bahl@kaagazuae.com